

1     IN THE CLAIMS

2     1 - 7   Previously Canceled

3  
4     8.     (Currently Amended) A method for recovering material from a tire portion containing a  
5           steel component, the method comprising the steps of:

- 6           (a)     contacting a the tire portion with a molten reactant metal including aluminum  
7                   under conditions facilitating sufficient to allow the dissolution of steel into the  
8                   molten reactant metal, the contacting step being performed for a reaction period  
9                   sufficient to allow substantially all organic materials originally included in the tire  
10                  portion to react with the molten reactant metal but leaving the steel component  
11                  substantially intact;
- 12           (b)     containing the tire portion on a tire carrier during the time that the tire portion is  
13                  contacted by the molten reactant metal; and
- 14           (c)     removing the tire carrier and unreacted solids retained on the tire carrier from the  
15                  molten reactant metal immediately after the reaction period, the unreacted solids  
16                  including the steel component remaining after the tire portion has contacted the  
17                  molten reactant metal for the reaction period.

18  
19     9.     (Previously Added) The method of Claim 8 further comprising the step of maintaining the  
20           temperature of the molten reactant metal at a minimum of approximately 800 degrees  
21           Celsius during the reaction period.

1      10.    (Previously Added) The method of Claim 8 wherein the steps of contacting the tire  
2           portion with the molten reactant metal and containing the tire portion on the tire carrier  
3           include:

- 4           (a)    lowering the tire portion into the molten reactant metal on the tire carrier; and  
5           (b)    pressing the tire portion into the molten reactant metal with a tire contactor  
6           member extending across an area above the tire carrier.

7  
8      11.    (Previously Added) The method of Claim 10 wherein the step of removing unreacted  
9           solids from the molten reactant metal includes:

- 10          (a)    lifting the tire contactor member and the tire carrier from the molten reactant  
11           metal and allowing the molten reactant metal to drain from around the unreacted  
12           solids, tire contactor member, and tire carrier; and  
13          (b)    cooling the tire carrier and unreacted solids located on the tire carrier.

14  
15      12.    (Previously Amended) A method for recovering materials from a tire portion including  
16           steel, the method comprising the steps of:

- 17          (a)    immersing the tire portion in a molten reactant metal including aluminum for a  
18           reaction period sufficient to allow substantially all organic materials originally  
19           included in the tire portion to react with the molten reactant metal, the molten  
20           reactant metal being held at a temperature at which steel dissolves therein;  
21          (b)    containing the tire portion on a tire carrier when the tire portion is immersed in the  
22           molten reactant metal; and

(c) removing the tire carrier and unreacted solids retained on the tire carrier from the molten reactant metal upon completion of the reaction period, the unreacted solids including steel remaining after the tire portion has contacted the molten reactant metal for the reaction period.

13. (Previously Added) The method of Claim 12 further comprising the step of maintaining the temperature of the molten reactant metal at a minimum of approximately 800 degrees Celsius during the reaction period.

14. (Previously Added) The method of Claim 12 wherein the steps of immersing the tire portion in the molten reactant metal and containing the tire portion on the tire carrier include:

- (a) lowering the tire portion into the molten reactant metal on the tire carrier; and
- (b) pressing the tire portion into the molten reactant metal with a tire contactor member extending across an area above the tire carrier.

15. (Previously Added) The method of Claim 12 wherein the step of removing unreacted solids from the molten reactant metal includes:

- (a) lifting the tire carrier from the molten reactant metal and allowing the molten reactant metal to drain from around the unreacted solids and tire carrier; and
- (b) cooling the tire carrier and unreacted solids located on the tire carrier.

1 16. (Previously Added) A method of recovering materials from a tire portion having a steel  
2 component, the method comprising the steps of:

3 (a) placing the tire portion in contact with a molten reactant metal while the molten  
4 reactant metal is maintained at a minimum temperature of approximately 800  
5 degrees Celsius so that organic components of the tire portion react with the  
6 molten reactant metal to produce liberated carbon and so that any part of the steel  
7 component that comes in contact with the molten reactant metal begins to dissolve  
8 into the molten reactant metal;

9 (b) collecting the liberated carbon together with gasses escaping from the molten  
10 reactant metal; and

11 (c) retrieving the remaining steel component of the tire portion from the molten  
12 reactant metal.  
13

14 17. (Previously Added) The method of Claim 16 wherein the step of placing the tire portion  
15 in contact with the molten reactant metal includes loading the tire portion into a tire  
16 carrier, positioning the tire carrier over the reactant metal, and then lowering the tire  
17 carrier vertically to immerse the tire carrier and tire portion in the molten reactant metal.  
18

19 18. (Previously Added) The method of Claim 16 wherein the step of collecting liberated  
20 carbon includes defining a gas collection hood area between a surface of the molten  
21 reactant metal and a hood member after the tire portion has been placed in contact with  
22 the molten reactant metal and collecting the liberated carbon in the gas collection hood  
23 area together with gasses escaping from the molten reactant metal.

- 1 19. (Previously Added) The method of Claim 16 further including the step of circulating the  
2 molten reactant metal around the tire portion while the tire portion is immersed in the  
3 molten reactant metal.  
4